

## HP1717 –Soya Long Oil Alkyd

### General Information:

HP1717 is a long oil alkyd made with soya oil in low odour mineral spirits (up to 7% aromatic content). It has been formulated for use in wood and metal coatings and architectural enamels. This product exhibits low yellowing, good gloss, and good overall appearance.

### Product Features:

- Good gloss and gloss retention
- Good colour retention
- Soluble in a wide range of solvents
- Good pigment dispersion

### Product Specifications:

- |                                  |   |
|----------------------------------|---|
| • Solvent                        | Low aromatic mineral spirits (< 7% aromatics) |
| • Nonvolatile by Mass (% Solids) | 70.00% ± 2.00%                                |
| • Brookfield Viscosity at 25°C   | 30 – 65 poise                                 |
| • Colour (Gardner)               | 8 max   |
| • Acid value                     | 20.0 max                                      |

### Typical Applications:

- Wood and metal coatings
- Gloss enamels (exterior and interior)

**Storage:** Product has an expected shelf life of 1 year. Exposure to humid conditions or elevated temperatures may affect physical properties of the material over time, shortening shelf life.

**SDS:** Please refer to the SDS for additional information on safe handling of this material.

NON-WARRANTY, The information presented in this publication is based upon the research and experience of HP Polymers Ltd. and is to the best of its knowledge accurate; however, no guarantee of its accuracy is made. Since HP Polymers Ltd. Has no control over the conditions under which its products may be employed; and since information as to the physiological and other properties is incomplete, HP Polymers Ltd. cannot guarantee the results obtained and assumes no liability whatsoever for possible damage or injury whether or not caused by the use of any products or processes mentioned herein. HP Polymers Ltd. will not be liable for resulting or consequential damage. This publication is not to be taken as a license to operate under, or recommendation to infringe upon any patents.